

Technical specifications :				
Nominal diameter in mm (tolerance +0/-5%)	6	8	10	12
Strength daN at 25% stretch	2.3	3.1	4.8	7
Strength daN at 50% stretch	2.9	4.0	6.1	9.4
Strength daN at 75% stretch	3.6	5.0	7.5	11.4
Strength daN at 100% stretch	4.3	5.9	9	13.7
Strength at break daN	46	110	145	192
Stretch at break %	260	265	280	277
Tolerance on strength and stretch +/- 15%				
Usage recommended 25 to 75% stretch				